



中国认可
国际互认
检测
TESTING
CNAS L6760

报告编号 HAPTX2502004232

第 1 页 共 5 页

检测报告

Test Report

产品名称
(Sample Name)

LSB 高强欧松板

委托单位
(Applicant)

永普庆雅(菏泽)木业有限公司

检验类别
(Testing Category)

委托检验

江苏环谱检测技术服务有限公司

JIANGSU HAP TESTING SERVICE CO., LTD

检验检测专用章



江苏环谱检测技术服务有限公司
JIANGSU HAP TESTING SERVICE CO., LTD
地址: 扬州市经济技术开发区吴州东路 198 号
Address: NO. 198 Wuzhou East Road, economic and technological development zone, YangZhou



中国认可
国际互认
检测
TESTING
CNAS L6760

检测报告

报告编号 HAPTX2503006730

第 2 页 共 5 页

申请单位 永善庆雅(菏泽)木业有限公司
地 址 山东省菏泽市曹县庄寨镇王庄村 92 号
生产厂家 德国 AEGOG (北碧府工厂)
地 址 泰国北碧府喃玛堪迪县 (Dan Makham Tia)

样品信息

样品名称 LSB 高强欧松板
样品品牌 德国 AEGOG
型号规格

*以上信息内容由申请人提供并确认

样品接受日期 2025-02-18
样品测试日期 2025-02-18—2025-03-10

检测要求 根据客户要求，参照 GB/T 11718-2021 进行检测。

检测结果 见后续页

签

发

授权签字人

签发日期: 2025年03月10日





中国认可
国际互认
检测
TESTING
CNAS L6760

检测报告

报告编号 HAPTX2503006730

第 3 页 共 5 页

检测结果:

序号	检测项目	单位	检测指标	检测结果	判定	
1	静曲强度	MPa	≥ 24	25	合格	
2	弹性模量	MPa	≥ 2300	3188	合格	
3	内结合强度	MPa	≥ 0.45	0.59	合格	
4	24h 吸水厚度膨胀率	%	≤ 12.0	6.2	合格	
5	含水率	%	3.0~13.0	7.1	合格	
6	板内密度偏差	%	± 10	0	合格	
7	表面胶合强度	MPa	≥ 0.60	1.12	合格	
8	表面耐冷热循环	—	无裂缝、鼓泡、变色、起皱等	符合	合格	
9	表面耐划痕	—	$\geq 1.5N$ 表面无大于 90% 的连续划痕	符合	合格	
10	表面耐磨	磨损值	mg/100r	≤ 80	51	合格
		表面情况 (图案纹)	—	磨 100r 后应保留 50% 以上花纹	符合	
11	表面耐香烟灼烧	级	达到 4 级以上 (5 级最好, 1 级最差)	4	合格	
12	表面耐干热	级	达到 4 级以上 (5 级最好, 1 级最差)	5	合格	
13	表面耐污染腐蚀 (图案纹)	级	达到 5 级以上 (5 级最好, 1 级最差)	5	合格	
14	表面耐电裂	级	达到 4 级以上 (5 级最好, 1 级最差)	4	合格	





中国认可
国际互认
检测
TESTING
CNAS L6760

检测报告

报告编号 HAPTX2502004232

第 4 页 共 5 页

序号	检测项目	单位	检测指标	检测结果	判定	
15	表面耐水蒸气	级	到 4 级以上 (5 级最好, 1 级最差)	4	合格	
16	甲醛释放量 (气候箱法)	mg/m ³	ENF 级 ≤ 0.025	未检出	合格	
17	挥发性有机化合物 (72h)	苯	μg/m ³	≤ 10	未检出	合格
		甲苯	μg/m ³	≤ 20	未检出	合格
		二甲苯	μg/m ³	≤ 20	未检出	合格
		TVOC	μg/m ³	≤ 100	未检出	合格

报告结束



中国认可
国际互认
检测
TESTING
CNAS L6760

检测报告

报告编号 HAPTX2502004232

第 5 页 共 5 页

注意事项 Notice Items

1、本报告无批准人签字、报告专用章及骑缝章无效。

This report shall be invalid without the signature of the approver, the special seal for the report and the cross-page seal.

2、本报告不得擅自修改、增加或删除。

This report shall not be modified, added or deleted without authorization.

3、报告结果只对本次受检样品负责。若对检测结果有异议，请在报告签发日期后十五天内书面提出，逾期不予受理。

The results of the report are only responsible for the samples tested this time. If there is any objection to the test result, please submit it in writing within fifteen days after the date of issuance of the report. Overdue will not be accepted.

4、未经环谱检测书面同意，不得部分复制本报告，亦不可作为宣传品使用。

Without the written consent of HAP, this report shall not be partially copied or used as publicity materials.

5、当需要结果符合性评价时，若客户无要求，一般不考虑结果的测量不确定度的影响。

When the result conformity evaluation is required, if the customer does not require it, the influence of the measurement uncertainty of the result is generally not considered.

6、此报告无 CMA 标识时，检测数据仅限科研、教学、内部质量控制或研发等活动使用。

When the report has not CMA logo, the test data is limited to scientific research, teaching, internal quality control or research and development activities.

7、本公司出具纸质正版报告与电子数字签名版具备相同效力，当两者内容有差异时以电子数字签名版为准。

The company's paper genuine report has the same legal effect as the electronic digital signature version. When the contents are different, subject to electronic digital signature version.

江苏环谱检测技术服务有限公司

JIANGSU HAP TESTING SERVICE CO., LTD

地址：扬州市经济技术开发区吴州东路 198 号

Address: NO. 198 Wuzhou East Road, economic and technological development zone, Yangzhou